









### 3D PRINTING WITH HIGH-STRENGTH PLASTICS



Polyamide (PA) plastics are materials that feature long-term stability and resistance to stress. They are also highly resistant to many chemicals and are available in nearly all colours. We can produce impermeable objects on request. In addition to unfilled plastics, PROTIQ also uses filled, soft and hightemperature plastics.

MATERIAL				PA 12	PA 12 GF	Alumide	TPU-80
							
	properties	test method	unit				
general properties	colour	–	–	white	beige/grayish	gray/silver	weiß
	base material	–	–	PA 12	PA 12 + glass beads	PA 12 + Aluminium	TPU
	density, laser-sintered	–	g/cm <sup>3</sup>	0,9-1,0	1,2-1,3	1,36-1,4	1,1 – 1,2
	surface roughness (Ra/Rz)	–	µm	8-11 / 50-70	6-7 / 40-50	5-7 / 25-40	13-17 / 72-84
mechanical properties	hardness (Shore A/D)	ISO 868	–	75±2 D	80 D	76 D	80 A
	flexural modulus	DIN EN ISO 178	MPa	1.500	2600 – 2.900*	3.600	–
	flexural strength	DIN EN ISO 178	MPa	58	73 – 78,3	72	–
	tensile modulus	DIN EN ISO 527	MPa	1.700 ± 150*	2800 – 3.200*	3.800	55
	tensile strength	DIN EN ISO 527	MPa	45 – 50*	45 – 53*	48	5,5 – 8
	ball indentation hardness	DIN EN ISO 2039	N/mm <sup>2</sup>	78	–	–	–
	elongation at break	DIN EN ISO 527	%	15 ± 10	5 – 9*	4	300 – 550
	Izod impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	32,8 ± 3,4	15 – 21*	–	–
	Izod notched impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	4,4 ± 0,4	4 – 4,2*	–	–
	Charpy notched impact strength	DIN EN ISO 179/1eA	kJ/m <sup>2</sup>	4,8 ± 0,3	4,1 – 5,4*	4,6	–
Charpy impact strength	DIN EN ISO 179/1eU	kJ/m <sup>2</sup>	53 ± 3,8	21,8 – 35*	29	–	
thermal properties	melting point	EN ISO 11357-1	°C	176	176	176	–
	temperature of deflection (1,80 MPa)	ISO 75-1/-2	°C	70	96 – 101	144	–
	temperature of deflection (0,45 MPa)	ISO 75-1/-2	°C	(0,65 MPa) 154	157 – 163	175	–
	Vicat softening temperature B/50	DIN EN ISO 306	°C	163	163 – 166	169	–
	Vicat softening temperature A/50	DIN EN ISO 306	°C	–	175 – 179	–	–
electrical properties	volume resistivity	DIN 53482 ICE-Publ. 92	Ω*cm	10 <sup>13</sup> – 10 <sup>15</sup>	–	3E+12	–
	surface resistivity	DIN 53482 ICE-Publ. 92	Ω	10 <sup>13</sup>	–	5E+14	–
	dielectrical strength	DIN 53481	kV/mm	92	–	0,1	–

MATERIAL				PA 11	PA 11 Black	PA11 ESD	PEEK HP3
							
	properties	test method	unit				
general properties	colour	–	–	white	black	grey-black	–
	base material	–	–	PA 11	PA 11	PA 11	PAEK
	density, laser-sintered	–	g/cm <sup>3</sup>	1,02	1,02	0,89 – 0,93	1,31
	surface roughness (Ra/Rz)	–	µm	6–10 / 35–45	6–10 / 35–45	6–10 / 35–45	–
mechanical properties	hardness (Shore A/D)	ISO 868	–	–	–	–	–
	flexural modulus	DIN EN ISO 178	MPa	1250 – 1300*	–	1250 – 1500*	–
	flexural strength	DIN EN ISO 178	MPa	–	–	–	–
	tensile modulus	DIN EN ISO 527	MPa	1.100 – 1.250*	1.600 – 1.900*	1400	4.250
	tensile strength	DIN EN ISO 527	MPa	45 – 46*	41 – 49*	28	90
	ball indentation hardness	DIN EN ISO 2039	N/mm <sup>2</sup>	–	–	–	–
	elongation at break	DIN EN ISO 527	%	31 – 45*	6 – 22*	10 – 30*	2,8
	Izod impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	No break – 86*	–	16 – 24*	–
	Izod notched impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	5,2 – 7,7*	–	3,0 – 3,5*	–
	Charpy notched impact strength	DIN EN ISO 179/1eA	kJ/m <sup>2</sup>	4,5 – 8,3*	–	3,2 – 3,3*	–
Charpy impact strength	DIN EN ISO 179/1eU	kJ/m <sup>2</sup>	85 – 198*	–	20 – 29*	–	
thermal properties	melting point	EN ISO 11357-1	°C	203	185	140	372
	temperature of deflection (1,80 MPa)	ISO 75-1/-2	°C	76	84	62	165
	temperature of deflection (0,45 MPa)	ISO 75-1/-2	°C	176	154	102	–
	Vicat softening temperature B/50	DIN EN ISO 306	°C	177	–	90	–
	Vicat softening temperature A/50	DIN EN ISO 306	°C	191	–	131	–

Dear PROTIQ customer, all information given is based on our knowledge and experience at the time of publication. In addition, the material properties can be influenced by component geometry, environmental influences and material additives. The stated material or component properties, as well as their suitability for specific applications, are neither agreed nor guaranteed, despite regular quality controls. The customer is responsible for checking the component properties and suitability for a specific application.

\* The mechanical properties may vary, depending on x-, y- and z-position of the test object and illumination parameters.

MATERIAL				PA 6X	PA 2210 FR
					
	properties	test method	unit		
general properties	colour	–	–	white	white
	base material	–	–	PA 6X	PA 12
	density, laser-sintered	–	g/cm <sup>3</sup>	1,00 – 1,04	1,06
	roughness (Ra/Rz)	–	µm	5–10 / 30–50	6–10 / 30–55
mechanical properties	hardness (Shore A/D)	ISO 868 / *ISO 7619-1	–	78 D	79 D
	flexural modulus	DIN EN ISO 178	MPa	–	2300
	flexural strength	DIN EN ISO 178	MPa	–	65
	tensile modulus	DIN EN ISO 527	MPa	2200 – 2500*	2.200 – 2.500*
	tensile strength	DIN EN ISO 527	MPa	54 – 60*	38 – 46*
	ball indentation strength	DIN EN ISO 2039	N/mm <sup>2</sup>	–	–
	elongation at break	DIN EN ISO 527	%	15–25*	3–7*
	Izod impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	–	–
	Izod notched impact strength	DIN EN ISO 180	kJ/m <sup>2</sup>	–	–
	Charpy notched impact strength	DIN EN ISO 179/1eA	kJ/m <sup>2</sup>	–	–
	Charpy impact strength	DIN EN ISO 179/1eU	kJ/m <sup>2</sup>	–	–
thermal properties	melting point	EN ISO 11357-1	°C	215	185
	temperature of deflection (1,80 MPa)	ISO 75-1/-2	°C	–	–
	temperature of deflection (0,45 MPa)	ISO 75-1/-2	°C	–	–
	Vicat softening temperature B/50	DIN EN ISO 306	°C	–	–
	Vicat softening temperature A/50	DIN EN ISO 306	°C	–	–

Dear PROTIQ customer, all information given is based on our knowledge and experience at the time of publication. In addition, the material properties can be influenced by component geometry, environmental influences and material additives. The stated material or component properties, as well as their suitability for specific applications, are neither agreed nor guaranteed, despite regular quality controls. The customer is responsible for checking the component properties and suitability for a specific application.

\* The mechanical properties may vary, depending on x-, y- and z-position of the test object and illumination parameters.

flammability PA 2241 FR					
	result	testing standard	method	ignition time	
flammability	passed	CS 25/JAR25/ FAR 25 § 25-853	–	12s	1,0 mm
	passed		–		1,5 mm
	passed		–		2,0 mm
	passed		–	60s	1,0 mm
	passed		–		1,5 mm
	passed		–		2,0 mm
flue gas density	passed	ABD 0031 (Issue:F)	AITM 2.0007	–	1,0 mm
	passed			–	1,5 mm
	passed			–	2,0 mm
toxicity	passed	ABD 0031 (Issue:F)	AITM 3.0005	–	1,0 mm
	passed			–	1,5 mm
	passed			–	2,0 mm
flammability PA 2210 FR					
	result	testing standard	method	ignition time	
flammability	passed	CS 25/JAR25/ FAR 25 § 25-853	–	12s	1,7 mm
	passed		–		2,0 mm
flammability	passed	UL 94	HB	–	0,75 mm
	passed	UL 94	V-0	–	3,0 mm
flue gas density	passed	ABD 0031 (Issue:F)	AITM 2.0007	–	1,7 mm
	passed			–	2,0 mm
toxicity	passed	ABD 0031 (Issue:F)	AITM 3.0005	–	1,7 mm
	passed			–	2,0 mm
approval specifications: JAR 25, UL 94					

Dear PROTIQ customer, all information given is based on our knowledge and experience at the time of publication. In addition, the material properties can be influenced by component geometry, environmental influences and material additives. The stated material or component properties, as well as their suitability for specific applications, are neither agreed nor guaranteed, despite regular quality controls. The customer is responsible for checking the component properties and suitability for a specific application.